forbo MOVEMENT SYSTEMS

siegling proposition
timing belts

Coating Data Sheet



Designation	
Coating type description OLD	V/20/FG; FG
Coating type description NEW	PVC 65/FG

Design	
Coating Material	PVC
Colour	White
Surface pattern	Herringbone profile

Technical data	
Hardness [Shore(A)]	65
Density [kg/m³]	
Coating thickness min. [mm]	3.0
Coating thickness max. [mm]	3.0
d factor *	30
Minimum pulley diameter D_{min} (approx.) [mm]	[d factor] x [selected coating thickness]
Minimum operating temperature [°C]	-10
Maximum operating temperature [°C]	80

Coefficient of static friction	
against PE foil	0.34
against wood	0.49
against sheet glass	0.70
against cardboard	0.46
against aluminium	0.58
against steel sheet	0.45

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations. Temperature range of polyurethane (PU) timing belt base material -5/+80 °C (permanent). See our brochure “Chemical resistance” which shows the resistances of Siegling Proposition (PU) timing belt base material.

Coating Data Sheet

Properties

Electrostatic properties	non-conductive
Wear resistance	medium
Compressibility	No
Product release properties	medium
Cleanability	effortful

Chemical restistance

General chemical resistance to	Acids, salts & bases

Special Fabrication

Sanding	No
Milling	No
Punching	Yes

Applications

Food packaging, Pharmaceutical industry, Glass conveying

General remarks

Food grade. Special Herringbone profile.

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations. Temperature range of polyurethane (PU) timing belt base material -5/+80 °C (permanent). See our brochure “Chemical resistance” which shows the resistances of Siegling Proposition (PU) timing belt base material.