forbo MOVEMENT SYSTEMS

siegling proposition
timing belts

Coating Data Sheet



Designation	
Coating type description OLD	Sylomer
Coating type description NEW	Sylomer - G

Design	
Coating Material	Polyurethane foam
Colour	Yellow
Surface pattern	Foam, closed cell

Technical data	
Hardness [Shore(A)]	
Density [kg/m³]	160
Coating thickness min. [mm]	6.0
Coating thickness max. [mm]	12.0
d factor *	10
Minimum pulley diameter D_{min} (approx.) [mm]	[d factor] x [selected coating thickness]
Minimum operating temperature [°C]	-30
Maximum operating temperature [°C]	70

Coefficient of static friction	
against PE foil	0.89
against wood	0.96
against sheet glass	1.24
against cardboard	0.70
against aluminium	1.12
against steel sheet	1.10

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations. Temperature range of polyurethane (PU) timing belt base material -5/+80 °C (permanent). See our brochure “Chemical resistance” which shows the resistances of Siegling Proposition (PU) timing belt base material.

Coating Data Sheet

Properties

Electrostatic properties	non-conductive
Wear resistance	low
Compressibility	Yes
Product release properties	low
Cleanability	effortful

Chemical restistance

General chemical resistance to	Generic fats and oils

Special Fabrication

Sanding	Yes
Milling	Yes
Punching	Yes

Applications

Bottle inspection lines, Glass conveying, Paper / Cardboard conveying

General remarks

Excellent cushioning and conforming to products. Cell structure open.

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations. Temperature range of polyurethane (PU) timing belt base material -5/+80 °C (permanent). See our brochure “Chemical resistance” which shows the resistances of Siegling Proposition (PU) timing belt base material.